

Hangzhou Vector Magnets Co., LTD

杭州矢量磁铁有限公司

Add: 88, Jiangling Rd, Binjiang, Hangzhou, Zhejiang, China

Tel: +86-571-5666-8956

Fax: +86-571-5666-8957

Url: www.vectormagnets.com



烧结铁氧体性能表

Sintered Hard Ferrite Magnetic Property Table

牌号 Grade	剩磁 Br Residual Induction				磁感矫顽力 HcB Coercive Force				内禀矫顽力 Hcj Intrinsic Coercive Force				最大磁能积 (BH)max Maximum Energy Products				Other Equivalent (Reference Only)
	mT		kGs		KA/m		KOe		KA/m		KOe		KJ/m3		MGOe		
	min	max	min	max	min	max	min	max	min	max	min	max	min	max	min	max	
Y8T	200	235	2.00	2.35	125	160	1.57	2.01	210	280	2.64	3.51	6.50	9.50	0.80	1.20	HF8/22, C1, FB1A
Y22H	310	360	3.10	3.60	220	250	2.76	3.14	280	320	3.51	4.02	20.00	24.00	2.50	3.00	HF20/28
Y25	360	400	3.60	4.00	135	170	1.70	2.14	140	200	1.76	2.51	22.50	28.00	2.80	3.50	HF25/14
Y26H-1	360	390	3.60	3.90	200	250	2.51	3.14	225	255	2.83	3.20	23.00	28.00	2.90	3.50	HF25/22
Y26H-2	360	380	3.60	3.80	263	288	3.30	3.62	318	350	3.99	4.40	24.00	28.00	3.00	3.50	HF24/35, C9, PMF-2BB, C7
Y27H	350	380	3.50	3.80	225	240	2.83	3.01	235	260	2.95	3.27	25.00	29.00	3.10	3.60	HF22/30
Y28	370	400	3.70	4.00	175	210	2.20	3.64	180	220	2.26	2.76	26.00	30.00	3.30	3.80	HF26/18, C5
Y28H-1	380	400	3.80	4.00	240	260	3.01	3.27	250	280	3.14	3.52	27.00	30.00	3.40	3.80	FB4B, C10
Y28H-2	360	380	3.60	3.80	271	295	3.40	3.70	382	405	4.80	5.08	26.00	30.00	3.30	3.80	FB6E, PMF-2BF
Y30H-1	380	400	3.80	4.00	230	275	2.89	3.46	235	290	2.95	3.64	27.00	32.50	3.40	4.10	HF26/26, C8, PMF-2BD
Y30H-2	395	415	3.95	4.15	275	300	3.45	3.77	310	335	3.89	4.20	27.00	32.00	3.40	4.00	HF26/30, PMF-2BE, FB5H, C12, PMF-5BE
Y32	400	420	4.00	4.20	160	190	2.01	2.39	165	195	2.07	2.45	30.00	33.50	3.80	4.20	HF32/17
Y32H-1	400	420	4.00	4.20	190	230	2.39	2.89	230	250	2.89	3.14	31.50	35.00	3.90	4.40	HF32/22, FB4D, C8B
Y32H-2	400	440	4.00	4.40	224	240	2.81	3.01	230	250	2.89	3.14	31.00	34.00	3.90	4.30	HF32/25, FB5N, PMF-7BB
Y33	410	430	4.10	4.30	220	250	2.76	3.14	225	255	2.83	3.20	31.50	35.00	3.90	4.40	C8B, PMF-2BB, FB4X, C11, PMF-6BB
Y33H	410	430	4.10	4.30	250	270	3.14	3.39	250	275	3.14	3.45	31.50	35.00	3.90	4.40	PMF-6BD, FB5B, PMF-5BD
Y34	420	440	4.20	4.40	200	230	2.51	2.89	205	235	2.57	2.95	32.50	36.00	4.10	4.40	C11, PMF-5BB
Y35	430	450	4.30	4.50	215	239	2.70	3.00	217	241	2.73	3.03	33.10	38.20	4.10	4.80	PMF-7BB
Y36	430	450	4.30	4.50	247	271	3.10	3.40	250	274	3.14	3.44	35.10	38.30	4.40	4.80	FB6N, PMF-7BD
Y38	440	460	4.40	4.60	285	305	3.58	3.83	294	310	3.69	3.89	36.60	40.60	4.60	5.10	FB9N, PMF-9BD
Y40	440	460	4.40	4.60	330	354	4.15	4.45	340	360	4.27	4.52	37.60	41.80	4.70	5.20	FB9B, PMF-9BE