



125SLR2 MONOCRYSTALLINE SILICON SOLAR CELLS



MECHANICAL DATA AND DESIGN


Format	125mm*125mm±0.5mm
Thickness	200um±30um
Format(-)	1.9mm bus bara(silver), blue anti-reflecting coating(silicon nitrid)
Back(+)	3mm wide soldering pads(silver),back surface field(aluminum)

TEMPERATURE COEFFICIENTS


Tk Voltage(-)	0.356%/K
Tk Current(+)	0.024%/K
Tk Power(-)	0.46%/K

No.	Efficiency (%)	Pmpp (W)	Ump (V)	Impp (A)	Uoc (V)	Isc (A)	FF (%)
10	18.20-18.40	2.82	0.53	5.317	0.63	5.685	78.69
09	18.00-18.20	2.79	0.527	5.292	0.628	5.669	78.34
08	17.80-18.00	2.76	0.524	5.264	0.626	5.648	78.02
07	17.60-17.80	2.73	0.522	5.231	0.624	5.634	77.67
06	17.40-17.60	2.7	0.519	5.202	0.623	5.621	77.1
05	17.20-17.40	2.66	0.515	5.169	0.621	5.591	76.67
04	17.00-17.20	2.63	0.512	5.14	0.62	5.571	76.19
03	16.80-17.00	2.6	0.508	5.114	0.619	5.551	75.61
02	16.60-16.80	2.57	0.506	5.078	0.618	5.527	75.29
01	16.00-16.60	2.52	0.502	5.015	0.616	5.496	74.48

IV CURVE



SPECTRAL RESPONSE



INTENSITY DEPENDENCE

Intensity [W/m ²]	Isc*	Voc*
1000	1.0	1.000
900	0.9	0.989
500	0.5	0.963
300	0.3	0.939
200	0.2	0.920

*Ratio of Voc(isc) at reduced intensity to Voc(isc) at 1000 W/m²

*calibrated against fraunhofer ISE freiburg