

TEST REPORT

NO.: A002R130328006-1R04

Date: Apr. 09, 2013

Page 1 of 3

Customer: Jiaxing Running Rubber&Plastic Co.,Ltd

Address: No. 168, Kangming East Road, Ganyao Town, Jiashan County, Jiaxing City, Zhejiang Province

Report on the submitted sample said to be

Sample name: dark blue, Orange

Model: RN-05, RN-06

Item/Lot No.: /

Material: EPDM

Buyer: /

Supplier: /

Manufacturer: /

Sample received date: Mar. 28, 2013

Testing period: From Mar. 28, 2013 to Apr. 09, 2013

Testing Requested:

As specified by client, do Ultra-Violet Light Resistance Test on the submitted samples.

Testing Method:

SAE J2020-2002

Results:

Please refer to next pages.

*****FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)*****

Signed for and on behalf of
Shenzhen AOV Testing Technology Co., Ltd, Kunshan Branch

Project Leader: Winnie
Yin Ying, Winnie
Physics Test Director

Reviewed by: Weikin
Wang Weixin, Weikin
Technical Director

Approved by: Mickey
Yuan Qi, Mickey
Lab Manager

TEST REPORT

NO.: A002R130328006-1R04

Date: Apr. 09, 2013

Page 2 of 3

Testing Parting:

1. Laboratory temperature and humidity

Temperature	23°C ± 2°C
Humidity	50% RH ± 5%RH

2. Testing condition:

- 2.1 Irradiance: 0.48W/m² @310nm
- 2.2 Light temperature: 70°C, 光照 8h
- 2.3 Dark temperature: 50°C, 黑暗 4h
- 2.4 Test time: 90h

3. Testing Equipment:

Light aging test chamber

4. Testing Results:

Sample name	Result description	Gray card rating (D65 lamphouse)
dark blue	After test, there was no blistering, obvious fading or other abnormal phenomenon found on sample	Grade 4-5
Orange	After test, there was no blistering, obvious fading or other abnormal phenomenon found on sample	Grade 4-5

Note:

- For more details see sample test photos.


TEST REPORT

NO.: A002R130328006-1R04

Date: Apr. 09, 2013

Page 3 of 3

Testing photo:



End of Report