

TEST REPORT

NO.: A002R130226003-1R04

Date: Mar. 01, 2013

Page 1 of 3

Customer: Jiaxing Running Rubber&Plastic Co.,Ltd

Address: No. 168, Kang Ming East Road, Ganyao Town, Jiashan County, Jiaxing City, Zhejiang Province

Report on the submitted sample said to be

Sample name: YELLOW EPDM GRANULES

Model: RN-04

Item/Lot No.: /

Material: /

Buyer: /

Supplier: /

Manufacturer: /

Sample received date: Feb. 26, 2013

Testing period: From Feb. 26, 2013 to Mar. 01, 2013

Testing Requested:

As specified by client, to determine the Fluorine, Chlorine, Bromine and Iodine content in the submitted sample.

Testing Method:

Testing Item	Testing method	Measuring instrument
Fluorine/ Chlorine/ Bromine/ Iodine	BS EN 14582: 2007	IC

Results:

Please refer to the next pages.

******FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)*****

Signed for and on behalf of Shenzhen AOV Testing Technology Co., Ltd, Kunshan Branch

Project Leader:

Li Tingting, Maggie **Chemical Test Director**

Reviewed by: Weikin

Wang Weixin, Weikin Technical Director Approved by: _______





TEST REPORT


NO.: A002R130226003-1R04

Date: Mar. 01, 2013

Page 2 of 3

Testing Flow:

To Determine Fluorine, Chlorine, Bromine and Iodine Content:



Testing Results:

Item	Unit	MQL	Limit	Result
Fluorine (F)	mg/kg	50	S. S. S.	N.D.
Chlorine (Cl)	mg/kg	50	900	507
Bromine (Br)	mg/kg	50	900	N.D.
lodine (I)	mg/kg	50	Se 1	N.D.
Total (Br+ Cl)	mg/kg	" Start	1500	507

Note:

-N.D.=not detected(<MQL)

-MQL=Method Quantitation Limit

-Photo is included





TEST REPORT

NO .: A002R130226003-1R04

Date: Mar. 01, 2013

Page 3 of 3

Photograph of Sample



End of Report



SHENZHEN AOV TESTING TECHNOLOGY CO.,LTD.KUNSHAN BRANCH No 8 Minguan Road, Zhoushi Town, Kunshan City, Jiangsu Province, China Tel :+86-512-5510 8000 Fax +86-512-5510 8808 Http://www.aovt.com Postcode 215300 (Attention is drawn to the terms and conditions printed overleaf)