



TEST REPORT

No.:SST18005304R1

Date.:2018-08-08

Page 1 of 3

Applicant: EURO TECH PLASTIC MFG(SHENZHEN) CO.,LTD

Address: NO482, JINBI ROAD, BILING, PINGSHAN, SHENZHEN, CHINA

Report on the submitted sample said to be:

Material description: LANYARD

Style/ Model No.:	LANYARD #200C	P/O No./ Lot No. :	MA3363
Order No.:	CHI180726(2018/1907)	Material :	200C
Color:	POLYESTER	Test Request Age :	N/A
Manufactory :	N/A	Buyer :	MAPS
Country of Origin :	CHINA	Country of Export :	UK

Sample received date : August 6,2018

Sample test period : From August 6,2018 to August 8,2018

SUMMARY OF TEST RESULT(S)

Test Item(s)	Conclusion	Remark
Color fastness to perspiration	--	See Next Page
Color fastness to rubbing	--	See Next Page

*****FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)*****

Signatories:

John Yue
Lab Manager



Hotline: 400-800-3625

Sharp Standard Testing Technology Co., Ltd

No.42 HouJie Road East, HouJie Town, DongGuan, Guangdong, China
Mail:sst@sst-test.com Tel: 86-769-87050530 Fax: 86-769-89026586



TEST REPORT

No.:SST18005304R1

Date.:2018-08-08

Page 2 of 3

Test Item (Unit)	Test Method (parameter)	Requirement (Remark)	Test Result	Conclusion
Color fastness to perspiration (Grade)	ISO 105 E04:2013	--	Alkali: Color Change 4.5 Color Staining -Acetate 4.0 -Cotton 4.5 -Polyamide 4.0 -Polyester 4.0 -Acrylic 4.0 -Wool 4.0 Acid: Color Change 4.5 Color Staining -Acetate 4.0 -Cotton 4.5 -Polyamide 4.0 -Polyester 4.5 -Acrylic 4.5 -Wool 4.5	--
Color fastness to rubbing (Grade)	ISO 105 X12:2016	--	Dry 4.5 Wet 4.5	--
Remark	This report is to supersede the report No.SST18005304 (Date: August 8, 2018).			



Hotline: 400-800-3625

Sharp Standard Testing Technology Co., Ltd

No.42 HouJie Road East, HouJie Town, DongGuan, Guangdong, China
 Mail:sst@sst-test.com Tel: 86-769-87050530 Fax: 86-769-89026586



TEST REPORT

No.:SST18005304R1

Date.:2018-08-08

Page 3 of 3

Photograph of Sample



*** End of Report ***

The test report is considered invalidated without both signature and specialized stamp, The result(s) shown in this test report refer only to the sample(s) tested. Without written approval of SST, this test report shall not be copied except in full .Detailed description are available at the website <http://www.sst-test.com>.



Hotline: 400-800-3625

Sharp Standard Testing Technology Co., Ltd

No.42 HouJie Road East, HouJie Town, DongGuan, Guangdong, China
Mail:sst@sst-test.com Tel: 86-769-87050530 Fax: 86-769-89026586