

Hangzhou Vector Magnets Co., LTD

杭州矢量磁铁有限公司

Add: 88, Jiangling Rd, Binjiang, Hangzhou, Zhejiang, China

Tel: +86-571-5666-8956

Fax: +86-571-5666-8957

Url: www.vectormagnets.com



NdFeB Rubber Magnets

Grade	剩磁 Br Residual Induction				矫顽力 Hcb Coercive Force				内禀矫顽力 Hcj Intrinsic Coercive Force				最大磁能积 (BH)max Maximum Energy Product				工作温度 Tw Working Temperature	硬度 Hardness		剩磁温度系 数 α Br Temperature Coefficient
	mT		Gs		kA/m		Oe		kA/m		Oe		kJ/m ³		MGOe		°C	Hv		%/°C
	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max	Min	Max	max	Min	Max	Typ.
VRN1	260	280	2600	2800	183	199	2300	2500	239	358	3000	4500	12.7	15.9	1.60	2.00	100	20	80	-0.016
VRN2	280	350	2800	3500	199	279	2500	3500	358	518	4500	6500	15.9	22.3	2.00	2.80	100	20	80	-0.016
VRN3	350	400	3500	4000	239	279	3000	3500	478	598	6000	7500	22.3	27.8	2.80	3.50	100	20	80	-0.016
VRN4	400	460	4000	4600	263	318	3300	4000	558	676	7000	8500	27.8	35.8	3.50	4.50	100	20	80	-0.016
VRN5	460	500	4600	5000	295	334	3700	4200	638	740	8000	9300	35.8	42.1	4.50	5.30	100	20	80	-0.016
VRN6	500	550	5000	5500	311	350	3900	4400	678	756	8500	9500	42.1	49.3	5.30	6.20	100	20	80	-0.016