

Rubber Magnet (Flexible Magnet)

Flexible Rubber Magnets

牌号Grade	剩磁 Br Residual Induction				矫顽力 Hcb Coercive Force				内禀矫顽力 Hcj Intrinsic Coercive Force				最大磁能积 (BH)max Maximum Energy Product				拉伸强度 Tensile Strength	硬度 Hardness	密度 Density	工作温度 Tw Working Temperature
	mT		Gs		kA/m		Oe		kA/m		Oe		kJ/m ³		MGOe		kg/cm ²	A	g/cm ³	°C
	min	max	min	max	min	max	min	max	min	max	min	max	min	max	min	max	min	min		max
FM1	140	180	1400	1800	105	130	1313	1625	160	238	2000	2975	4	6.4	0.50	0.80	20	90	3.6 - 3.8	-40 - 85
FM2	180	210	1800	2100	130	151	1625	1888	175	286	2188	3575	6.4	8.8	0.80	1.10	20	90	3.6 - 3.8	-40 - 85
FM3	180	220	1800	2200	110	143	1375	1788	143	191	1788	2388	5.6	8.8	0.70	1.10	20	95	3.6 - 3.8	-40 - 85
FM4	210	250	2100	2500	151	179	1888	2238	191	319	2388	3988	8.8	12	1.10	1.50	20	90	3.6 - 3.8	-40 - 85
FM5	220	240	2200	2400	128	151	1600	1888	159	207	1988	2588	8.8	11.2	1.10	1.40	20	95	3.6 - 3.8	-40 - 85
FM6	240	270	2400	2700	151	179	1888	2238	191	238	2388	2975	11.2	13.6	1.40	1.70	20	95	3.6 - 3.8	-40 - 85
FM7	240	270	2400	2700	151	179	1888	2238	191	238	2388	2975	11.2	13.6	1.40	1.70	20	95	3.6 - 3.8	-40 - 100
FM8	240	270	2400	2700	151	179	1888	2238	191	238	2388	2975	11.2	13.6	1.40	1.70	15	95	3.6 - 3.8	-40 - 85
FM9	240	265	2400	2650	151	179	1888	2238	191	238	2388	2975	11.2	13.2	1.40	1.65	15	95	3.6 - 3.8	-40 - 85
FM14-1	270	330	2700	3300	143	191	1788	2388	207	318	2588	3975	12	20	1.50	2.50	10	80~100	3.8 - 4.4	-40 - 80
FM14-2	330	390	3300	3900	191	223	2388	2788	318	478	3975	5975	20	28	2.50	3.50	10	80~100	4.2 - 4.8	-40 - 80
FM14-3	390	480	3900	4800	207	270	2588	3375	478	717	5975	8963	28	36	3.50	4.50	10	80~100	4.5 - 5.0	-40 - 80
FM14	390	480	3900	4800	207	270	2588	3375	478	717	5975	8963	28	36	3.50	4.50	10	80~100	4.5 - 5.0	-40 - 80
FM15	240	270	2400	2700	160	183	2000	2288	215	263	2688	3288	11.6	13.6	1.45	1.70	15	95	3.6 - 3.8	-40 - 100

