



Standard Specification for High-Strength Low-Alloy Structural Steel¹

This standard is issued under the fixed designation A 242/A 242M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers high-strength low-alloy structural steel shapes, plates, and bars for welded, riveted, or bolted construction intended primarily for use as structural members where savings in weight [mass] or added durability are important. The atmospheric corrosion resistance of the steel in most environments is substantially better than that of carbon structural steels with or without copper addition. When properly exposed to the atmosphere, this steel can be used bare (unpainted) for many applications (see Note 1). This specification is limited to material up to 4 in. [100 mm], inclusive, in thickness.

NOTE 1—For methods of estimating the atmospheric corrosion resistance of low-alloy steels, see Guide G 101.

1.2 When the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized. See Appendix X3 of Specification A 6/A 6M for information on weldability.

1.3 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.4 For structural products produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification A 6/A 6M apply.

2. Referenced Documents

2.1 ASTM Standards:²

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys, and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock, and Ships.

Current edition approved April 1, 2004. Published May 2004. Originally approved in 1941. Last previous edition approved in 2003 as A 242/A 242M – 03a.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

G 101 Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels

3. General Requirements for Delivery

3.1 Structural products furnished under this specification shall conform to the requirements of the current edition of Specification A 6/A 6M, for the specific structural product ordered, unless a conflict exists, in which case this specification shall prevail.

3.2 Coils are excluded from qualification to this specification until they are processed into a finished structural product. Structural products produced from coil means structural products that have been cut to individual lengths from a coil. The processor directly controls, or is responsible for, the operations involved in the processing of a coil into a finished structural product. Such operations include decoiling, leveling or straightening, hot-forming or cold-forming (if applicable), cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 2—For structural products produced from coil and furnished without heat treatment or with stress relieving only, two test results are to be reported for each qualifying coil. Additional requirements regarding structural products produced from coil are described in Specification A 6/A 6M.

4. Materials and Manufacture

4.1 The steel shall be semi-killed or killed.

5. Chemical Composition

5.1 The heat analysis shall conform to the requirements prescribed in Table 1.

5.2 The steel shall conform on product analysis to the requirements prescribed in Table 1, subject to the product analysis tolerances in Specification A 6/A 6M.

5.3 Choice and use of alloying elements, combined with carbon, manganese, phosphorus, sulfur, and copper within the limits prescribed in 5.1 to give the mechanical properties prescribed in Section 6 and to provide the atmospheric corrosion resistance of 1.1, shall be made by the manufacturer and

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Tensile Requirements

	Plates and Bars ^A			Structural Shapes		
	For thick- nesses $\frac{3}{4}$ in. [20 mm], and under	For thick- nesses over $\frac{3}{4}$ to $1\frac{1}{2}$ in. [20 to 40 mm], incl	For thick- nesses over $1\frac{1}{2}$ to 4 in. [40 to 100 mm], incl	For flange or leg thicknesses 1.5 in. [40 mm] and under	For flange thicknesses over 1.5 in. [40 mm] to 2 in. [50 mm], incl	For flange thicknesses over 2 in. [50 mm]
Tensile strength, min, ksi [MPa]	70 [480]	67 [460]	63 [435]	70 [485]	67 [460]	63 [435]
Yield point, min, ksi [MPa]	50 [345]	46 [315]	42 [290]	50 [345]	46 [315]	42 [290]
Elongation in 8 in. [200 mm], min, %	18 ^{B,C}	18 ^{B,C}	18 ^{B,C}	18 ^C	18	18
Elongation in 2 in. [50 mm], min, %	21 ^C	21 ^C	21 ^C	21	21	21 ^D

^ASee the Orientation subsection in the Tension Tests section of Specification A 6/A 6M.

^BElongation not required to be determined for floor plate.

^CFor plates wider than 24 in. [600 mm] the elongation requirement is reduced two percentage points. See the Elongation Requirement Adjustments subsection in the Tension Tests section of Specification A 6/A 6M.

^DFor wide flange shapes over 426 lb/ft [634 kg/m], elongation in 2 in. [50 mm] of 18 % minimum applies.

included and reported in the heat analysis to identify the type of steel applied. Elements commonly added include: chromium, nickel, silicon, vanadium, titanium, and zirconium.

5.4 The atmospheric corrosion-resistance index, calculated on the basis of the heat analysis of the steel, as described in Guide G 101—Predictive Method Based on the Data of Larabee and Coburn, shall be 6.0 or higher.

NOTE 3—The user is cautioned that the Guide G 101 predictive equation (Predictive Method Based on the Data of Larabee and Coburn) for calculation of an atmospheric corrosion-resistance index has only been verified for the composition limits stated in the guide.

5.5 When required, the manufacturer shall supply evidence of corrosion resistance satisfactory to the purchaser.

6. Tension Test

6.1 The material as represented by the test specimens shall conform to the requirements as to tensile properties prescribed in Table 2.

7. Keywords

7.1 atmospheric corrosion resistance; bars; bolted construction; durability; high-strength; low-alloy; plates; riveted construction; shapes; steel; structural steel; weight; welded construction

TABLE 2 Chemical Requirements (Heat Analysis)

Element	Composition, %
	Type 1
Carbon, max	0.15
Manganese, max	1.00
Phosphorus, max	0.15
Sulfur, max	0.05
Copper, min	0.20

SUPPLEMENTARY REQUIREMENTS

Standardized supplementary requirements for use at the option of the purchaser are listed in Specification A 6/A 6M. Those that are considered suitable for use with this specification are listed by title:

- | | |
|--|-------------------------------------|
| S2. Product Analysis, | S6. Drop-Weight Test, |
| S3. Simulated Post-Weld Heat Treatment of Mechanical Test Coupons, | S8. Ultrasonic Examination, and |
| S5. Charpy V-Notch Impact Test, | S15. Reduction of Area Measurement. |
| | S32. Single Heat Bundles. |

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A 242/A 242M – 03a) that may impact the use of this standard (approved April 1, 2004).

(I) Added Supplementary Requirement S32.

Committee A01 has identified the location of selected changes to this standard since the last issue (A 242/A 242M-03) that may impact the use of this standard (approved May 10, 2003).

(I) Table 1 was revised.

Committee A01 has identified the location of selected changes to this standard since the last issue (A 242/A 242M-01) that may impact the use of this standard (approved April 10, 2003).

(I) 1.4, 3.1, 3.1.1 (renumbered as 3.2), and Note 2 have been revised to be consistent with the terminology and requirements of A 6/A 6M.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).