



CERTIFICATE

By Authority Of THE UNITED STATES OF AMERICA Legally Binding Document

By the Authority Vested By Part 5 of the United States Code § 552(a) and Part 1 of the Code of Regulations § 51 the attached document has been duly **INCORPORATED BY REFERENCE** and shall be considered legally binding upon all citizens and residents of the United States of America. ***HEED THIS NOTICE:*** Criminal penalties may apply for noncompliance.



Document Name: ASTM A618: Hot-Formed Welded and Seamless High-Strength Low-Alloy Structural Tubing

CFR Section(s): 24 CFR 200, Subpart S

Standards Body: American Society for Testing and Materials



Official Incorporator:

THE EXECUTIVE DIRECTOR
OFFICE OF THE FEDERAL REGISTER
WASHINGTON, D.C.



Standard Specification for HOT-FORMED WELDED AND SEAMLESS HIGH- STRENGTH LOW-ALLOY STRUCTURAL TUBING¹

This Standard is issued under the fixed designation A 618; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal.

1. Scope

1.1 This specification covers three grades of hot-formed welded and seamless high-strength low-alloy square, rectangular, round, or special shape structural tubing for welded, riveted, or bolted construction of bridges and buildings and for general structural purposes. When the steel is used in welded construction, the welding procedure shall be suitable for the steel and the intended service.

1.2 When enhanced corrosion resistance is desired for Grades I and III, copper limits may be specified.

NOTE—The values stated in U.S. customary units are to be regarded as the standard.

2. Ordering Information

2.1 Orders for material under this specification shall include the following as required to describe the material adequately:

2.1.1 Quantity (feet or number of lengths),

2.1.2 Grade (Tables 1 and 2),

2.1.3 Material (round, square, or rectangular tubing),

2.1.4 Method of manufacture (seamless, butt-welded, or hot-stretch-reduced electric-resistance welded),

2.1.5 Size (outside diameter and nominal wall thickness for round tubing and the outside dimensions and calculated nominal wall thickness for square and rectangular tubing),

2.1.6 Length (specific or random, see 7.2),

2.1.7 End condition (see 8.2),

2.1.8 Burr removal (see 8.2),

2.1.9 Certification (see 11.1),

2.1.10 Specification number,

2.1.11 End use, and

2.1.12 Special requirements.

3. Manufacture

3.1 The steel shall be made by one or more of the following processes: open-hearth, basic-oxygen, or electric-furnace.

3.2 The tubing shall be made by the seamless, furnace-butt-welded (continuous-welded), or hot-stretch-reduced electric-resistance-welded process.

4. Chemical Requirements

4.1 When subjected to the heat and product analysis, respectively, the steel shall conform to the requirements prescribed in Table 1.

4.1.1 For Grade I, the choice and use of alloying elements, combined with carbon, manganese, and sulfur within the limits prescribed in Table 1 to give the mechanical properties prescribed in Table 2, shall be made by the manufacturer and included and reported in the heat analysis for information purposes only to identify the type of steel applied.

4.1.2 The chemistry may be such as to provide copper-bearing steel having enhanced corrosion resistance of twice the atmospheric corrosion resistance of plain carbon steel.

4.1.3 The copper limits of Grade I are subject to negotiation and shall be indicated in the purchase order.

4.1.4 When Grade III is required for enhanced corrosion resistance, copper limits may be specified and the minimum content shall be 0.20 percent by heat analysis and

¹ This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.09 on Pipe.

Current edition approved July 29, 1974. Published September 1974. Originally published as A 618 - 68. Last previous edition A 618 - 73.



0.18 percent by product analysis.

4.2 *Heat Analysis*—An analysis of each heat of open-hearth, basic-oxygen, or electric-furnace steel shall be made by the manufacturer. This analysis shall be made from a test ingot taken during the pouring of the heat. The chemical composition thus determined shall conform to the requirements specified in Table 1 for heat analysis.

4.3 *Product Analysis:*

4.3.1 An analysis may be made by the purchaser from finished tubing manufactured in accordance with this specification, or an analysis may be made from flat-rolled stock from which the welded tubing is manufactured. When product analyses are made, two sample lengths from a lot of each 500 lengths or fraction thereof shall be selected. The specimens for chemical analysis shall be taken from the sample lengths in accordance with the applicable procedures of ASTM Method E 59, Sampling Steel and Iron for Determination of Chemical Composition.² The chemical composition thus determined shall conform to the requirements specified in Table 1 for product analysis.

4.3.2 In the event the chemical composition of one of the sample lengths does not conform to the requirements shown in Table 1 for product analysis, an analysis of two additional lengths selected from the same lot shall be made, each of which shall conform to the requirements shown in Table 1 for product analysis, or the lot is subject to rejection.

5. Mechanical Requirements

5.1 *Tensile Properties:*

5.1.1 The material, as represented by the test specimen, shall conform to the requirements prescribed in Table 2.

5.1.2 Elongation may be determined on a gage length of either 2 in. (or 50 mm) or 8 in. (200 mm) at the manufacturer's option.

5.1.3 For material under $\frac{5}{16}$ in. (7.94 mm) in thickness, a deduction from the percentage elongation of 1.25 percentage points in 8 in. specified in Table 2 shall be made for each decrease of $\frac{1}{32}$ in. (0.79 mm) of the specified thickness under $\frac{5}{16}$ in. (7.94 mm).

5.2 *Bend Test*—The bend test specimen shall stand being bent cold through 180 deg

without cracking on the outside of the bent portion, to an inside diameter which shall have a relation to the thickness of the specimen as prescribed in Table 3.

5.3 *Number of Tests*—Two tension and two bend tests, as specified in 5.4.2, and 5.4.3, shall be made from tubing representing each heat. However, if tubing from one heat differs in the ordered nominal wall thickness, one tension test and one bend test shall be made from both the heaviest and lightest wall thicknesses processed.

5.4 *Test Specimens:*

5.4.1 The test specimens required by this specification shall conform to those described in the latest issue of ASTM Methods and Definitions A 370, for the Mechanical Testing of Steel Products.³

5.4.2 The tension test specimen shall be taken longitudinally from a section of the finished tubing, at a location 90 deg from the weld in the case of welded tubing, and shall not be flattened between gage marks. If desired, the tension test may be made on the full section of the tubing; otherwise, a longitudinal strip-test specimen shall be used as prescribed in Methods A 370, Supplement II. The specimens shall have all burrs removed and shall not contain surface imperfections which would interfere with proper determination of the tensile properties of the metal.

5.4.3 The bend test specimen shall be taken longitudinally from the tubing, and shall represent the full wall thickness of material. The sides of the bend test specimen may have the corners rounded to a maximum radius of $\frac{1}{16}$ in. (1.59 mm).

5.5 *Test Methods:*

5.5.1 The yield point shall be determined in accordance with one of the alternatives described in Methods A 370.

5.5.2 The bend test shall be made on square or rectangular tubing manufactured in accordance with this specification.

6. Retests

6.1 If the results of the mechanical tests representing any heat do not conform to a

² Annual Book of ASTM Standards, Part 12.

³ Annual Book of ASTM Standards, Parts 1, 2, 3, 4, 5, and 10.

requirement, as specified in 5.1 and 5.2, retests may be made on additional tubing of double the original number from the same heat, each of which shall conform to the requirement specified, or the tubing represented by the test is subject to rejection.

6.2 In case of failure on retest to meet the requirements of 5.1 and 5.2, the manufacturer may elect to retreat, rework, or otherwise eliminate the condition responsible for failure to meet the specified requirements. Thereafter, the material remaining from the respective heat originally represented may be tested, and shall comply with all requirements of this specification.

7. Dimensions and Permissible Variations

7.1 The dimensions of square, rectangular, round, and special shape structural tubing to be ordered under this specification shall be subject to prior negotiation with the manufacturer. The dimensions agreed upon shall be indicated in the purchase order.

7.2 Permissible Variations:

7.2.1 Outside Dimensions:

7.2.1.1 For round tubing 2 in. and over in nominal diameter, the outside diameter shall not vary more than ± 1 percent from the specified outside diameter. For sizes $1\frac{1}{2}$ in. (38.1 mm) and under, the outside diameter shall not vary more than $\frac{1}{64}$ in. (0.40 mm) over and more than $\frac{1}{32}$ in. (0.79 mm) under the specified outside diameter.

7.2.1.2 The specified dimensions, measured across the flats at positions at least 2 in. (50.8 mm) from either end of square and rectangular tubing and including an allowance for convexity and concavity, shall not exceed the plus and minus tolerance shown in Table 4.

7.2.2 *Mass*—The mass of structural tubing shall not be less than the specified value by more than 3.5 percent. The mass tolerance shall be determined from individual lengths or for round tubing sizes $4\frac{1}{2}$ in. (114 mm) in outside diameter and under and square and rectangular tubing having a periphery of 14 in. (356 mm) and under shall be determined from masses of the customary lifts produced by the mill. On round tubing sizes over $4\frac{1}{2}$ in. in outside diameter and square and rectangular tubing having a periphery in excess of 14 in. the mass tolerance is applicable to the

individual length.

7.2.3 *Length*—Structural tubing is commonly produced in random mill lengths of 16 to 22 ft (4.9 to 6.7 m) or 32 to 44 ft (9.8 to 13.4 m), in multiple lengths, and in definite cut lengths (Section 2). When cut lengths are specified for structural tubing, the length tolerances shall be in accordance with Table 5.

7.2.4 *Straightness*—The permissible variation for straightness of structural tubing shall be $\frac{1}{8}$ in. times the number of feet of total length divided by 5 (2.08 mm times length in meters).

7.2.5 *Squareness of Sides*—For square or rectangular structural tubing, adjacent sides may deviate from 90 deg. by a tolerance of ± 2 deg. max.

7.2.6 *Radius of Corners*—For square or rectangular structural tubing, the radius of any outside corner of the section shall not exceed 3 times the specified wall thickness.

7.2.7 Twist:

7.2.7.1 The tolerance for twist, or variation with respect to axial alignment of the section for square, rectangular, or special shape structural tubing, shall be as prescribed in Table 6.

7.2.7.2 Twist is measured by holding down one end of a square or rectangular tube on a flat surface plate with the bottom side of the tube parallel to the surface plate, and noting the height that either corner at the opposite end of the bottom side of the tube extends above the surface plate. The difference in the height of the corners shall not exceed the values in Table 6.

8. Workmanship and Quality Levels

8.1 The structural tubing shall be free from injurious defects and shall have a commercially smooth finish.

8.1.1 Surface imperfections shall be classed as injurious defects when their depth exceeds 15 percent of the specified wall thickness and when the imperfections materially affected the appearance of the structural member, or when their length (measured in a transverse direction) and depth would materially reduce the total cross-sectional area at any location.

8.1.2 Injurious defects having a depth not in excess of $3\frac{1}{8}$ percent of the wall thickness may be repaired by welding, subject to the following conditions:



8.1.2.1 The defect shall be completely removed by chipping or grinding to sound metal.

8.1.2.2 The repair weld shall be made using suitable coated electrodes.

8.1.2.3 The projecting weld metal shall be removed to produce a workmanlike finish.

8.2 The ends of structural tubing, unless otherwise specified, shall be finished square cut, and the burr held to a minimum. The burr can be removed on the outside diameter, inside diameter, or both, as a supplementary requirement. When the burrs are to be removed, it shall be specified in the purchase order.

9. Packaging, Marking, and Loading

9.1 Except as noted in 9.2, each length of structural tubing shall be legibly marked by rolling, die stamping, ink printing, or paint stenciling to show the following information: manufacturer's name, brand, or trademark; size and wall thickness; steel grade; and the specification number.

9.2 For structural tubing 1½ in. (38.1 mm) and under in nominal size or the greatest cross sectional dimension less than 2 in. (50.8 mm), the information listed in 9.1 may be marked on a tag securely attached to each bundle.

9.3 When specified in the order, contract, etc., packaging, marking, and loading shall be in accordance with the procedures recommended by ASTM Recommended Practice A 700, for Packaging, Marking, and Loading Methods for Steel Products for Domestic Shipment.⁴

10. Inspection

10.1 All tubing shall be subject to an inspection at the place of manufacture to assure conformance with the requirements of this specification.

11. Certification

11.1 Upon request of the purchaser in the contract or order, a manufacturer's certification that the material was manufactured and tested in accordance with this specification together with a report of the chemical and tensile tests shall be furnished.

12. Rejection

12.1 Each length of tubing received from the manufacturer may be inspected by the purchaser and, if it does not meet the requirements of this specification based on the inspection and test method as outlined in the specification, the length may be rejected and the manufacturer shall be notified. Disposition of rejected tubing shall be a matter of agreement between the manufacturer and the purchaser.

12.2 Tubing found in fabrication or in installation to be unsuitable for the intended use, under the scope and requirements of this specification, may be set aside and the manufacturer notified. Such tubing shall be subject to mutual investigation as to the nature and severity of the deficiency and the forming or installation, or both, conditions involved. Disposition shall be a matter for agreement.

⁴ Annual Book of ASTM Standards, Parts 1, 3, 4, and 5.

TABLE 1 Chemical Requirements

Element	Composition, percent					
	Grade I		Grade II		Grade III	
	Heat	Product	Heat	Product	Heat	Product
Carbon, max	0.22	0.26	0.22	0.26	0.23	0.27
Manganese	1.25 max	1.30 max	0.85-1.25	1.30 max	1.35 max	1.40 max
Phosphorus, max	0.04	0.05	0.04	0.05
Sulfur, max	0.05	0.063	0.05	0.063	0.05	0.06
Silicon, max	0.30	0.33	0.30	0.35
Copper, min	0.20	0.18
Vanadium, min	0.02	0.01	0.02 ^a	0.01

^a For Grade III, columbium may be used in conformance with the following limits: 0.005 percent, min (heat) and 0.004 percent, min (product).

TABLE 2 Tensile Requirements

	Grade I		Grade II		Grade III	
Tensile strength, min, ksi (MPa)	70	(483)	70	(483)	65	(448)
Yield point, min, ksi (MPa)	50	(345)	50	(345)	50	(345)
Elongation in 2 in. or 50 mm, min, percent	22		22		20	
Elongation in 8 in. or 200 mm, min, percent	19		18		18	

TABLE 3 Bend Test Requirements

Thickness of Material, in. (mm)	Ratio of Bend Diameter to Specimen Thickness
3/4 (19.05) and under	1
Over 3/4 to 1 (19.05 to 25.4), incl	1 1/2
Over 1 (25.4)	2

TABLE 5 Cut Length Tolerances for Structural Tubing

	22 ft (6.71 m) and Under		Over 22 to 44 ft (6.71 to 13.42 m), incl	
	Over	Under	Over	Under
Length tolerance for specified cut lengths, in. (mm)	1/2 (12.7)	1/4 (6.35)	3/4 (19.05)	1/4 (6.35)

TABLE 4 Outside Dimension Tolerances for Square, Rectangular, and Special Shape Structural Tubing

Largest Outside Dimension Across Flats, in. (mm)	Tolerance Plus and Minus, in. (mm)
2 1/2 (63.5) and under	0.020 (0.51)
Over 2 1/2 to 3 1/2 (63.5 to 88.9), incl	0.025 (0.64)
Over 3 1/2 to 5 1/2 (88.9 to 139.7), incl	0.030 (0.76)
Over 5 1/2 (139.7)	1 percent

TABLE 6 Twist Tolerances for Square, Rectangular, or Special Shape Structural Tubing

Specified Dimension of Longest Outside Side, in. (mm)	Maximum Twist per 3 ft of Length, in.	Maximum Twist per Meter of Length, mm.
1 1/2 (38.1) and under	0.050	1.39
Over 1 1/2 to 2 1/2 (38.1 to 63.5), incl	0.062	1.72
Over 2 1/2 to 4 (63.5 to 101.6), incl	0.075	2.09
Over 4 to 6 (101.6 to 152.4), incl	0.087	2.42
Over 6 to 8 (152.4 to 203.2), incl	0.100	2.78
Over 8 (203.2)	0.112	3.11

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 1916 Race St., Philadelphia, Pa. 19103, which will schedule a further hearing regarding your comments. Failing satisfaction there, you may appeal to the ASTM Board of Directors.