

Flat products made of steels for pressure purposes —

Part 4: Nickel alloy steels with specified low temperature properties

The European Standard EN 10028-4:2003 has the status of a
British Standard

ICS 77.140.30; 77.140.50

National foreword

This British Standard is the official English language version of EN 10028-4:2003. It supersedes BS EN 10028-4:1995 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/73/2, Steel plates and bars for pressure purposes, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard, was published under the authority of the Standards Policy and Strategy Committee on 24 June 2003

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 12, an inside back cover and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

© BSI 24 June 2003

English version

Flat products made of steels for pressure purposes - Part 4: Nickel alloy steels with specified low temperature properties

Produits plats en aciers pour appareils à pression - Partie
4: Aciers alliés au nickel avec caractéristiques spécifiées à
basse température

Flacherzeugnisse aus Druckbehälterstählen - Teil 4:
Nickellegierte kaltzähe Stähle

This European Standard was approved by CEN on 20 February 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions.....	4
4 Dimensions and tolerances on dimensions.....	4
5 Calculation of mass	4
6 Classification and designation	4
6.1 Classification.....	4
6.2 Designation.....	4
7 Information to be supplied by the purchaser.....	4
7.1 Mandatory information	4
7.2 Options.....	5
7.3 Example for ordering.....	5
8 Requirements	5
8.1 Steelmaking process	5
8.2 Delivery condition.....	5
8.3 Chemical composition.....	5
8.4 Mechanical properties	7
8.5 Surface condition.....	9
8.6 Internal soundness	9
9 Inspection	9
9.1 Types of inspection and inspection documents	9
9.2 Tests to be carried out	9
9.3 Retests	9
10 Sampling.....	9
11 Test methods.....	9
12 Marking	9
Annex A (informative) Guidelines for heat treatment	10
Annex ZA (informative) Clauses of this European Standard addressing essential requirements or other provisions of EU Directives	11
Bibliography	12

Foreword

This document (EN 10028-4:2003) has been prepared by Technical Committee ECISS /TC 22, "Steels for pressure purposes - Qualities", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2003, and conflicting national standards shall be withdrawn at the latest by December 2003.

This document supersedes EN 10028-4:1994.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

EN 10028 consists of the following parts under the general title *Flat products made of steels for pressure purposes*:

Part 1: General requirements

Part 2: Non-alloy and alloy steels with specified elevated temperature properties

Part 3: Weldable fine grain steels, normalized

Part 4: Nickel alloy steels with specified low temperature properties

Part 5: Weldable fine grain steels, thermomechanically rolled

Part 6: Weldable fine grain steels, quenched and tempered

Part 7: Stainless steels

NOTE The clauses marked by two points (••) contain information relating to agreements that may be made at the time of enquiry and order.

Annex A is for information only.

This document includes a Bibliography.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies requirements for flat products for pressure equipment made of nickel alloy steels as specified in Table 1.

The requirements and definitions of EN 10028-1 also apply.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 10028-1:2000 + A1:2002, *Flat products made of steels for pressure purposes – Part 1: General requirements.*

EN 10204, *Metallic products – Types of inspection documents.*

3 Terms and definitions

For the purposes of this European Standard the terms and definitions given in EN 10028-1 apply.

4 Dimensions and tolerances on dimensions

See EN 10028-1.

5 Calculation of mass

See EN 10028-1.

6 Classification and designation

6.1 Classification

In accordance with EN 10020, all steel grades covered by this European Standard are alloy special steels.

6.2 Designation

See EN 10028-1.

7 Information to be supplied by the purchaser

7.1 Mandatory information

See EN 10028-1.

7.2 Options

A number of options are specified in this standard and listed below. Additionally the relevant options of EN 10028-1 apply. If the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the products shall be supplied in accordance with the basic specification (see also EN 10028-1).

- a) delivery condition other than that specified in Table 3 (see 8.2.2);
- b) delivery of products in the untreated condition (see 8.2.3);
- c) mid thickness test pieces for the impact test (see clause 10);
- d) verification of impact energy for longitudinal test pieces (see clause 11).

7.3 Example for ordering

10 plates with nominal dimensions, thickness = 50 mm, width = 2 000 mm, length = 10 000 mm, made of a steel grade with the name 15NiMn6 and the number 1.6228 as specified in EN 10028-4, to be delivered with inspection document 3.1.B as specified in EN 10204.

10 plates – 50 x 2000 x 10 000 – EN 10028-4 15NiMn6 – Inspection document 3.1.B

or

10 plates – 50 x 2000 x 10 000 – EN 10028-4 1.6228 – Inspection document 3.1.B.

8 Requirements

8.1 Steelmaking process

See EN 10028-1.

8.2 Delivery condition

8.2.1 The delivery condition shall be noted in the inspection document.

8.2.2 •• Unless otherwise agreed at the time of enquiry and order, the products covered by this standard shall be supplied in the usual delivery conditions specified in Table 3.

8.2.3 •• If so agreed at the time of enquiry and order, the products may be supplied in the untreated condition.

In these cases, the specified tests shall be carried out on test pieces in the usual delivery condition as given in Table 3.

NOTE Testing in a simulated heat treated condition does not discharge the processor from the obligation of providing proof of the specified properties in the finished product.

8.3 Chemical composition

8.3.1 The requirements of Table 1 shall apply for the chemical composition according to the cast analysis.

8.3.2 The product analysis shall not deviate from the specified values for the cast analysis as specified in Table 1 by more than the values given in Table 2.

Table 1 — Chemical composition (cast analysis) ^a

Steel grade		% by mass									
Steel name	Steel number	C max.	Si max.	Mn	P max.	S max.	Al _{total} min.	Mo max.	Nb max.	Ni	V max.
11MnNi5-3	1.6212	0,14	0,50	0,70 to 1,50	0,025	0,015	0,020	-	0,05	0,30 ^b to 0,80	0,05
13MnNi6-3	1.6217	0,16	0,50	0,85 to 1,70	0,025	0,015	0,020	-	0,05	0,30 ^b to 0,85	0,05
15NiMn6	1.6228	0,18	0,35	0,80 to 1,50	0,025	0,015	-	-	-	1,30 to 1,70	0,05
12Ni14	1.5637	0,15	0,35	0,30 to 0,80	0,020	0,010	-	-	-	3,25 to 3,75	0,05
X12Ni5	1.5680	0,15	0,35	0,30 to 0,80	0,020	0,010	-	-	-	4,75 to 5,25	0,05
X8Ni9	1.5662	0,10	0,35	0,30 to 0,80	0,020	0,010	-	0,10	-	8,50 to 10,00	0,05
X7Ni9	1.5663	0,10	0,35	0,30 to 0,80	0,015	0,005	-	0,10	-	8,50 to 10,00	0,01

^a Elements not listed in this table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate measures shall be taken to prevent the addition from scrap or other materials used in steelmaking of these elements which may adversely affect the mechanical properties and usability. The content of Cr + Cu + Mo shall not exceed 0,50 %.

^b For product thicknesses ≤ 40 mm, a minimum nickel content of 0,15 % is permitted.

Table 2 — Permissible product analysis tolerances on the limiting values given in Table 1 for the cast analysis

Element	Specified value in the cast analysis according to Table 1	Permissible deviation ^a of the product analysis
	% by mass	% by mass
C	$\leq 0,18$	+ 0,02
Si	$\leq 0,50$	+ 0,05
Mn	$\leq 1,00$	$\pm 0,05$
	$> 1,00$ to $\leq 1,70$	$\pm 0,10$
P	$\leq 0,015$	+ 0,003
	$> 0,015$ to $\leq 0,025$	+ 0,005
S	$\leq 0,015$	+ 0,003
Al	$\geq 0,020$	- 0,005
Mo	$\leq 0,10$	+ 0,03
Nb	$\leq 0,05$	+ 0,01
Ni	$\leq 0,85$	$\pm 0,05$
	$> 0,85$ to $\leq 3,75$	$\pm 0,07$
	$> 3,75$ to $\leq 10,00$	$\pm 0,10$
V	$\leq 0,05$	+ 0,01

^a If several product analyses are carried out on one cast, and the contents of an individual element determined lie outside the permission range of the chemical composition specified for the cast analysis, then it is only allowed to exceed the permissible maximum value or fall short of the permissible minimum value, but not both for one cast.

8.4 Mechanical properties

The values given in Tables 3 and 4 (see also EN 10028-1 and clause 10) shall apply.

Table 3 — Mechanical properties at room temperature

Steel grade		Usual delivery condition ^{a,b} (Heat treatment symbol)	Product thickness <i>t</i> mm	Yield strength <i>R_{eH}</i> MPa min.	Tensile strength <i>R_m</i> MPa	Elongation after fracture <i>A</i> % min.
Steel name	Steel number					
11MnNi5-3	1.6212	+N (+NT)	≤ 30	285	420 to 530	24
			30 < <i>t</i> ≤ 50	275		
			50 < <i>t</i> ≤ 80	265		
13MnNi6-3	1.6217	+N (+NT)	≤ 30	355	490 to 610	22
			30 < <i>t</i> ≤ 50	345		
			50 < <i>t</i> ≤ 80	335		
15NiMn6	1.6228	+N or +NT or +QT	≤ 30	355	490 to 640	22
			30 < <i>t</i> ≤ 50	345		
			50 < <i>t</i> ≤ 80	335		
12Ni14	1.5637	+N or +NT or +QT	≤ 30	355	490 to 640	22
			30 < <i>t</i> ≤ 50	345		
			50 < <i>t</i> ≤ 80	335		
X12Ni5	1.5680	+N or +NT or +QT	≤ 30	390	530 to 710	20
			30 < <i>t</i> ≤ 50	380		
X8Ni9 +NT640 ^a	1.5662 +NT640 ^a	+N plus +NT	≤ 30	490	640 to 840	18
			30 < <i>t</i> ≤ 50	480		
X8Ni9 +QT640 ^a	1.5662 +QT640 ^a	+QT	≤ 30	490		
			30 < <i>t</i> ≤ 50	480		
X8Ni9 +QT680 ^a	1.5662 +QT680 ^a	+QT ^c	≤ 30	585	680 to 820	18
			30 < <i>t</i> ≤ 50	575		
X7Ni9	1.5663	+QT ^c	≤ 30	585	680 to 820	18
			30 < <i>t</i> ≤ 50	575		

^a +N: normalized; +NT: normalized and tempered; +QT: quenched and tempered; +NT640/+QT640/+QT680: Heat treatment variant with minimum tensile strength of 640 MPa or 680 MPa.

^b For temperatures and cooling conditions, see Table A.1.

^c For product thickness < 15 mm, delivery conditions +N plus +NT are also applicable.

EN 10028-4:2003 (E)

Table 4 — Minimum impact energy values (valid for V-notched test pieces)

Steel grade		Heat treatment condition ^{a,b}	Product thickness mm	Direction	Minimum impact energy KV in J at a temperature in °C of											
Steel name	Steel number				20	0	-20	-40	-50	-60	-80	-100	-120	-150	-170	-196
11MnNi5-3	1.6212	+N (+NT)	5 ° to 80	longitudinal	70	60	55	50	45	40	-	-	-	-	-	
					50	50	45	35	30	27	-	-	-	-	-	
13MnNi6-3	1.6217	+N		longitudinal	65	65	65	60	50	40	-	-	-	-	-	
					50	50	45	40	35	27	-	-	-	-	-	
15NiMn6	1.6228	or +NT		transverse	65	60	55	55	50	45	40	-	-	-	-	
					50	50	45	40	35	27	-	-	-	-	-	
12Ni14	1.5637	or +NT		longitudinal	65	60	55	55	50	45	40	-	-	-	-	
					50	50	45	35	35	30	27	-	-	-	-	
X12Ni5	1.5680	or +QT		transverse	70	70	70	65	65	60	50	40 ^d	-	-	-	
					60	60	55	45	45	40	30	27 ^d	-	-	-	
X8Ni9+NT640; X8Ni9+QT640 ^a	1.5662+NT640; 1.5662+QT640 ^a	+N plus +NT; +QT		5 ° to 50	longitudinal	100	100	100	100	100	100	90	80	70	60	50
						70	70	70	70	70	70	60	50	45	40	
X8Ni9 +QT680 ^a	1.5662 +QT680 ^a	+QT	transverse		120	120	120	120	120	120	110	100	90	80	70	
					100	100	100	100	100	90	80	70	60	50		
X7Ni9	1.5663	+QT	longitudinal		120	120	120	120	120	120	120	120	120	120	110	100
					100	100	100	100	100	100	100	100	100	90	80	

^a +N: normalized and tempered; +NT: quenched and tempered; +QT: quenched and tempered; +NT640/+QT640/+QT680: Heat treatment variant with minimum tensile strength of 640 MPa or 680 MPa.

^b For temperatures and cooling conditions, see Table A.1.

^c See 10.2.2.3 in EN 10028-1:2000 + A1:2002.

^d The values are applicable for product thicknesses ≤ 25 mm at -110 °C and for product thicknesses of 25 mm < t ≤ 30 mm at -115 °C.

8.5 Surface condition

See EN 10028-1.

8.6 Internal soundness

See EN 10028-1.

For possible verification of internal soundness, see also EN 10028-1.

9 Inspection

9.1 Types of inspection and inspection documents

See EN 10028-1.

9.2 Tests to be carried out

See EN 10028-1.

9.3 Retests

See EN 10028-1.

10 Sampling

See EN 10028-1.

•• For the impact test, deviating from EN 10028-1:2000 + A1:2002, Figure 2, footnote f, the preparation of test pieces taken from the mid thickness may be agreed at the time of enquiry and order. In this case, test temperatures and minimum impact energy values shall also be agreed.

11 Test methods

See EN 10028-1.

•• For the impact test, verification of impact energy for longitudinal test pieces may be agreed at the time of enquiry and order in accordance with 10.2.2.3 and 11.4 in EN 10028-1:2000 + A1:2002.

12 Marking

See EN 10028-1.

NOTE For the grade X8Ni9 the relevant heat treatment variant (+NT640 or +QT640 or +QT680) belongs to the steel name or steel number.

Annex A (informative)

Guidelines for heat treatment

Reference data on heat treatment temperatures and cooling media are given in Table A.1.

Table A.1 — Guidelines on the temperatures and cooling media of heat treatment

Steel grade		Heat treatment condition ^a	Heat treatment			
Steel name	Steel number		Austenitizing °C	Cooling ^b	Tempering °C	Cooling ^b
11MnNi5-3	1.6212	+N (+NT)	880 to 940	a	580 to 640	a
13MnNi6-3	1.6217	+N (+NT)	880 to 940	a	580 to 640	a
15NiMn6	1.6228	+N	850 to 900	a	-	-
		+NT	850 to 900	a	600 to 660	a or w
		+QT	850 to 900	w or o	600 to 660	a or w
12Ni14	1.5637	+N	830 to 880	a	-	-
		+NT	830 to 880	a	580 to 640	a or w
		+QT	820 to 870	w or o	580 to 640	a or w
X12Ni5	1.5680	+N	800 to 850	a	-	-
		+NT	800 to 850	a	580 to 660	a or w
		+QT	800 to 850	w or o	580 to 660	a or w
X8Ni9 +NT640	1.5662 +NT640	+N plus +NT	880 to 930 + 770 to 830	a	540 to 600	a or w
X8Ni9 +QT640	1.5662 +QT640	+QT	770 to 830	a	540 to 600	a or w
X8Ni9 +QT680	1.5662 +QT680	+QT ^c	770 to 830	w or o	540 to 600	a or w
X7Ni9	1.5663	+QT ^c	770 to 830	w or o	540 to 600	a or w

^a +N: normalized; +NT: normalized and tempered; +QT: quenched and tempered; +NT640/+QT640/+QT680: Heat treatment variant with minimum tensile strength of 640 MPa or 680 MPa.

^b a: air; o: oil; w: water.

^c See Table 3, footnote c.

Annex ZA (informative)

Relationship between this European Standard and the Essential Requirements of EU Directive 97/23/EC

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association to provide a means of conforming to Essential Requirements of the New Approach Directive 97/23/EC.

Once this standard is cited in the Official Journal of the European Communities under that Directive and has been implemented as a national standard in at least one Member State, compliance with the clauses of this standard given in Table ZA.1 confers, within the limits of the scope of this standard, a presumption of conformity with the corresponding Essential Requirements of that Directive and associated EFTA regulations.

Table ZA.1 – Correspondence between this European Standard and Directive 97/23/EC

Clause(s)/sub clause(s)-of this EN	Essential Requirements (ERs) of Directive 97/23/EC
All normative clauses	Annex 1, section 4

WARNING: Other requirements and other EU Directives may be applicable to the product(s) falling within the scope of this standard.

Bibliography

- [1] EN 10020, *Definition and classification of grades of steel.*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.