

Flat products made of steels for pressure purposes —

Part 6: Weldable fine grain steels, quenched and tempered

The European Standard EN 10028-6:2003 has the status of a
British Standard

ICS 77.140.30; 77.140.50

National foreword

This British Standard is the official English language version of EN 10028-6:2003. It supersedes BS EN 10028-6:1997 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee ISE/73/2, Steel plates and bars for pressure purposes, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 12, an inside back cover and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

This British Standard, was published under the authority of the Standards Policy and Strategy Committee on 16 July 2003

© BSI 16 July 2003

ISBN 0 580 42264 X

EUROPEAN STANDARD

EN 10028-6

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2003

ICS 77.140.30; 77.140.50

Supersedes EN 10028-6:1996

English version

Flat products made of steels for pressure purposes - Part 6: Weldable fine grain steels, quenched and tempered

Produits plats en aciers pour appareils à pression - Partie
6: Aciers soudables à grains fins laminés trempés et
revenus

Flacherzeugnisse aus Druckbehälterstählen - Teil 6:
Schweißgeeignete Feinkornbaustähle, vergütet

This European Standard was approved by CEN on 17 January 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions.....	4
4 Dimensions and tolerances	4
5 Calculation of mass	4
6 Classification and designation	4
6.1 Classification.....	4
6.2 Designation.....	4
7 Information to be supplied by the purchaser.....	5
7.1 Mandatory information	5
7.2 Options.....	5
7.3 Example for ordering.....	5
8 Requirements	5
8.1 Steelmaking process	5
8.2 Delivery condition.....	5
8.3 Chemical composition.....	6
8.4 Mechanical properties	6
8.5 Surface condition.....	6
8.6 Internal soundness	6
9 Inspection	6
9.1 Types of inspections and inspections documents	6
9.2 Tests to be carried out	6
9.3 Retests	6
10 Sampling.....	6
11 Test methods.....	6
12 Marking	6
Annex ZA (informative) Clauses of this European Standard addressing essential requirements or other provisions of EU Directives.	12
Bibliography	12

Foreword

This document EN 10028-6:2003 has been prepared by Technical Committee ECISS /TC 22, "Steels for pressure purposes - Qualities", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2003, and conflicting national standards shall be withdrawn at the latest by December 2003.

This document supersedes EN 10028-6:1996.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative annex ZA, which is an integral part of this document.

This European Standard consists of the following parts, under the general title *Flat products made of steels for pressure purposes*:

Part 1: General requirements

Part 2: Non-alloy and alloy steels with specified elevated temperature properties

Part 3: Weldable fine grain steels, normalized

Part 4: Nickel alloy steels with specified low temperature properties

Part 5: Weldable fine grain steels, thermomechanically rolled

Part 6: Weldable fine grain steels, quenched and tempered

Part 7: Stainless steels

NOTE The clauses marked by two points (••) contain information relating to agreements that may be made at the time of enquiry and order.

This document includes a Bibliography.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the requirements for flat products for pressure equipments made of quenched and tempered steels as specified in Table 1.

The requirements in EN 10028-1 also apply.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 10020, *Definition and classification of grades of steels.*

EN 10028-1:2000 + A1:2002, *Flat products made of steels for pressure purposes – Technical delivery conditions - Part 1: General requirements.*

EN 10204, *Metallic products – Types of inspection documents.*

3 Terms and definitions

For the purposes of this European Standard the terms and definitions given in EN 10028-1 apply.

4 Dimensions and tolerances

See EN 10028-1.

5 Calculation of mass

See EN 10028-1.

6 Classification and designation

6.1 Classification

6.1.1 This standard covers the steel grades given in Table 1 in four qualities:

- a) the basic series (P...Q);
- b) series with elevated temperature properties (P...QH);
- c) series with low temperature properties down to -40 °C (P...QL1);
- d) series with low temperature properties down to -60 °C (P...QL2).

6.1.2 In accordance with EN 10020 all the steels specified in this standard are alloy special steels.

6.2 Designation

See EN 10028-1.

7 Information to be supplied by the purchaser

7.1 Mandatory information

See EN 10028-1.

7.2 Options

A number of options is specified in this standard and listed below. Additionally the relevant options of EN 10028-1 apply. If the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the products shall be supplied in accordance with the basic specification (see also EN 10028-1).

- a) mid thickness test pieces for the impact test (see clause 10);
- b) lower copper content and maximum tin content (see Table 1, footnote c);
- c) mechanical properties for thicknesses > 150 mm (see Table 3, footnote b);
- d) applicability of elevated temperature values for QL grades (see Table 5, footnote b).

7.3 Example for ordering

10 plates with nominal dimensions, thickness = 50 mm, width = 2 000 mm, length = 10 000 mm, made of a steel grade with the name P355QL2 and the number 1.8869 as specified in prEN 10028-6, inspection certificate 3.1B as specified in EN 10204:

10 plates – 50 x 2 000 x 10 000 – EN 10028-6 P355QL2 – Inspection certificate 3.1.B

or

10 plates – 50 x 2 000 x 10 000 – EN 10028-6 1.8869 – Inspection certificate 3.1.B

8 Requirements

8.1 Steelmaking process

See EN 10028-1.

8.2 Delivery condition

8.2.1 The products covered by this standard shall be supplied in the quenched and tempered condition.

8.2.2 The steels specified in this standard shall be suitable for welding processes in current use (see notes 1 to 3 to 8.2.3).

8.2.3 The manufacturer shall, if requested, provide the purchaser with data on suitable welding conditions determined on the basis of weld procedure tests.

NOTE 1 With increasing product thickness and strength level cold cracking can occur. Cold cracking is caused by the following factors in combination:

- the amount of diffusible hydrogen in the weld metal;
- brittle structure of the heat affected zone;
- tensile stress concentrations in the welded joint.

NOTE 2 When using recommendations as laid down, for example in EN 1011-1 and EN 1011-2, the recommended welding conditions and the various welding ranges of the steel grades can be determined depending on the product thickness, the applied welding energy, the design requirements, the electrode efficiency, the welding process and the weld metal properties.

EN 10028-6:2003 (E)

NOTE 3 Excessive post weld heat-treatment (PWHT) conditions can decrease the mechanical properties. It is therefore recommended that the purchaser seeks, at the time of enquiry and order, the advice of the manufacturer and considers, where appropriate, the verification of the mechanical properties on simulated post weld heat treated samples.

8.3 Chemical composition

8.3.1 The requirements of Table 1 apply for the chemical composition according to the cast analysis.

8.3.2 The product analysis may deviate from the specified values of the cast analysis given in Table 1 by the values given in Table 2.

8.4 Mechanical properties

The values given in Tables 3 to 5 apply (see also EN 10028-1 and clause 10).

8.5 Surface condition

See EN 10028-1.

8.6 Internal soundness

See EN 10028-1.

For possible verification of internal soundness, see also EN 10028-1.

9 Inspection

9.1 Types of inspections and inspections documents

See EN 10028-1.

9.2 Tests to be carried out

See EN 10028-1.

9.3 Retests

See EN 10028-1.

10 Sampling

See EN 10028-1.

For the impact test, deviating from EN 10028-1:2000 + A1:2002, Figure 2, footnote f, the preparation of test pieces taken from the mid thickness may be agreed at the time of enquiry and order. In this case, test temperatures and minimum impact energy values shall also be agreed.

11 Test methods

See EN 10028-1.

12 Marking

See EN 10028-1.

Table 1 — Chemical composition (cast analysis)^{a,b}

Steel grade		Maximum contents, % by mass														
name	number	C	Si	Mn	P	S	N	B	Cr	Mo	Cu ^c	Nb ^d	Ni	Ti ^d	V ^d	Zr ^d
P355Q	1.8866	0,16	0,40	1,50	0,025	0,015	0,015	0,005	0,30	0,25	0,30	0,05	0,50	0,03	0,06	0,05
P355QH	1.8867															
P355QL1	1.8868				0,020	0,010										
P355QL2	1.8869															
P460Q	1.8870	0,18	0,50	1,70	0,025	0,015	0,015	0,005	0,50	0,50	0,30	0,05	1,00	0,03	0,08	0,05
P460QH	1.8871															
P460QL1	1.8872				0,020	0,010										
P460QL2	1.8864															
P500Q	1.8873	0,18	0,60	1,70	0,025	0,015	0,015	0,005	1,00	0,70	0,30	0,05	1,50	0,05	0,08	0,15
P500QH	1.8874															
P500QL1	1.8875				0,020	0,010										
P500QL2	1.8865															
P690Q	1.8879	0,20	0,80	1,70	0,025	0,015	0,015	0,005	1,50	0,70	0,30	0,06	2,50	0,05	0,12	0,15
P690QH	1.8880															
P690QL1	1.8881				0,020	0,010										
P690QL2	1.8888															

^a Elements not listed in this table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate measures shall be taken to prevent the addition from scrap and other materials used in steelmaking of these elements which may adversely affect the mechanical properties and usability.

^b The manufacturer may add one or several alloying element(s) up to the maximum values specified in the order as a function of the product thickness and the steelmaking conditions in order to attain the specified properties. The chemical composition range for each manufacturer's analysis shall be given in the offer and confirmation of order.

^c •• For reasons of hot formability, a lower copper content and a maximum tin content may be agreed at the time of enquiry and order.

^d The percentage of grain refining elements shall be at least 0,015 %. Aluminium is also included in these elements. The minimum content of 0,015 % applies here to dissolved aluminium. This value is regarded as attained if the total aluminium content is at least 0,018 %; in cases of dispute, the dissolved aluminium content is to be determined.

Table 2 — Permissible deviations of the chemical composition in the results of the product analysis from the specified values applicable to the cast analysis

Element	Specified value in the cast analysis according to Table 1 % by mass	Permissible deviation ^a of the product analysis % by mass
C	≤ 0,20	+ 0,02
Si	≤ 0,80	+ 0,05
Mn	≤ 1,70	+ 0,10
P	≤ 0,025	+ 0,005
S	≤ 0,015	+ 0,003
Al _{total}	≥ 0,018	- 0,005
N	≤ 0,015	+ 0,002
B	≤ 0,005	+ 0,0005
Cr	≤ 1,50	+ 0,10
Mo	≤ 0,70	+ 0,04
Cu	≤ 0,30	+ 0,05
Ni	≤ 2,50	+ 0,10
Nb	≤ 0,06	+ 0,01
Ti	≤ 0,05	+ 0,01
V	≤ 0,12	+ 0,01
Zr	≤ 0,15	+ 0,01

^a If several product analysis are carried out on one cast, and then contents of an individual element determined lie outside the permissible range of the chemical composition specified for the cast analysis then it is only allowed to exceed the permissible maximum value or fall short of the permissible minimum value, but not both for one cast.

Table 3 — Mechanical properties at room temperature

Steel grade	name	number	Yield strength ^a R_{eH} for product thickness t in mm		Tensile strength R_m for product thickness t in mm		Elongation after fracture A % min.	
			$t \leq 50$	$50 < t \leq 100$ MPa min.	$t \leq 100$	$100 < t \leq 150^b$ MPa		
P355Q		1.8866						
P355QH		1.8867						
P355QL1		1.8868	355	335	315	490 to 630	450 to 590	22
P355QL2		1.8869						
P460Q		1.8870						
P460QH		1.8871	460	440	400	550 to 720	500 to 670	19
P460QL1		1.8872						
P460QL2		1.8864						
P500Q		1.8873						
P500QH		1.8874	500	480	440	590 to 770	540 to 720	17
P500QL1		1.8875						
P500QL2		1.8865						
P690Q		1.8879						
P690QH		1.8880	690	670	630	770 to 940	720 to 900	14
P690QL1		1.8881						
P690QL2		1.8888						

^a The yield strength to be determined shall be the upper yield strength R_{eH} or, if this is not pronounced, the 0,2 % proof strength $R_{p0.2}$.

^b •• Other product thicknesses may be agreed at the time of enquiry and order.

Table 4 — Impact energy (valid for transverse test pieces)

Steel grades	Product thickness mm	Impact energy KV J min. at a temperature in $^{\circ}C$ of				
		- 60	- 40	- 20	0	+ 20
P...Q P...QH	5 ^a to 150	-	-	27	40	60
P...QL1		-	27	40	60	-
P...QL2		27	40	60	80	-
^a See EN 10028-1.						

Table 5 — Minimum 0,2 % proof strength $R_{p0,2}$ at elevated temperatures^a

Steel grade ^b		Minimum 0,2 % proof strength $R_{p0,2}$ (MPa) values ^c at a temperature in $^{\circ}C$ of					
Name	Number	50	100	150	200	250	300
P355QH	1.8867	340	310	285	260	235	215
P460QH	1.8871	445	425	405	380	360	340
P500QH	1.8874	490	470	450	420	400	380
P690QH	1.8880	670	645	615	595	575	570
^a The values shall be proven by means of a tensile test at elevated temperature for the specified service temperature. An agreement at the time of enquiry and order shall be reached on this between the purchaser and manufacturer. ^b •• If agreed at the time of enquiry and order, these values also apply to the grades P...QL with specified low temperature properties. ^c These values are valid for product thicknesses $t \leq 50$ mm. For larger thicknesses, the minimum 0,2 % proof strength values are reduced by: - 20 MPa for $50 \text{ mm} < t \leq 100 \text{ mm}$ and by - 60 MPa for $t > 100 \text{ mm}$.							

ANNEX ZA

(informative)

Relationship between this European Standard and the Essential Requirements of EU Directive 97/23/EC

This European Standard has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association to provide a means of conforming to Essential Requirements of the New Approach Directive 97/23/EC.

Once this standard is cited in the Official Journal of the European Communities under that Directive and has been implemented as a national standard in at least one Member State, compliance with the clauses of this standard given in table ZA.1 confers, within the limits of the scope of this standard, a presumption of conformity with the corresponding Essential Requirements of that Directive and associated EFTA regulations.

Table ZA.1 – Correspondence between this European Standard and Directive 97/23/EC

Clause(s)/sub-clause(s) of EN 10028-6	Essential Requirements (ERs) of Directive 97/23/EC
All normative clauses	Annex 1, section 4

WARNING: Other requirements and other EU Directives may be applicable to the product(s) falling within the scope of this standard.

Bibliography

EN 1011-1, *Welding - Recommendations for welding of metallic materials – Part 1: General guidance for arc welding.*

EN 1011-2, *Welding - Recommendations for welding of metallic materials – Part 2: Arc welding of ferritic steels.*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.