



# DASHIQIAO YUTONG REFRACTORIES CO., LTD.

HETUN VILLAGE, GUANTUN TOWN, 115100 DASHIQIAO, YINGKOU, LIAONING, CHINA  
Tel: 0086-417-5616187/5616188/5616189      Email: yutong\_jessica@hotmail.com  
Web: www.yutongrefractory.com

Ref :

## TECHNICAL DATA SHEET

NAME	NORMAL FUSED MAGNESITE 98
CHEMICAL FORMULA	MGO
FORMULA WEIGH	40.3
SPECIFICATIONS	
MGO	98.0%MIN
SIO2	0.50%MAX
CAO	1.00%MAX
FE2O3	0.50%MAX
AL2O3	0.20%MAX
L.O.I	0.20%MAX
Bulk Density	3.50g/cm <sup>3</sup> MIN
Application: steel making, high grade magnesia bricks, magnesia carbon bricks, unshaped refractory materials, including gunning, ramming, repairing mass etc.	
The above mentioned product has no poison, no pollution and no cauterization. It's common chemical product.	

For and on behalf of  
Dashiqiao Yutong Refractories Co.Ltd  
大石桥宇通耐火材料有限公司  
**孟新宇**  
Authorized Signature(s)