



DASHIQIAO YUTONG REFRACTORIES CO., LTD.

HETUN VILLAGE, GUANTUN TOWN, 115100 DASHIQIAO, YINGKOU, LIAONING, CHINA
Tel: 0086-417-5616187/5616188/5616189 Email: yutong_jessica@hotmail.com
Web: www.yutongrefractory.com

Ref :

TECHNICAL DATA SHEET

NAME	Magnesite Carbon bricks LR-MT-14A
CHEMICAL FORMULA	MGO (%)
FORMULA WEIGH	≥76.0%
SPECIFICATIONS	
C	≥14.0%
A.P(%)	≤4.0%
Bulk Density g/cm ³	≥2.95
C.C.S (Mpa)	≥40.0
Hot modulus of rupture/MP 1400°C*30min	≥14.0

For and on behalf of
Dashiqiao Yutong Refractories Co.Ltd
大石桥宇通耐火材料有限公司
孟新宇
Authorized Signature(s)