



DASHIQIAO YUTONG REFRACTORIES CO., LTD.

HETUN VILLAGE, GUANTUN TOWN, 115100 DASHIQIAO, YINGKOU, LIAONING, CHINA
Tel: 0086-417-5616187/5616188/5616189 Email: yutong_jessica@hotmail.com
Web: www.yutongrefractory.com

Ref :

TECHNICAL DATA SHEET

Magnesite bricks

Brand	MZ-90	MZ-92	MZ-95	MZ-96	MZ-97
Index					
MgO(%)	≥90	≥92	≥95	≥96	≥97
SiO ₂ (%)	≤5.5	≤4.5	≤2.0	≤1.8	≤1.0
CaO (%)	≤3.0	≤2.0	≤2.0	≤1.8	≤1.0
A.P (%)	≤19	≤18	≤18	≤17	≤16
B.D(kg/m ³)	≥2.90`	≥2.92	≥2.95	≥3.00	≥3.05
Cold Crushing Strength (Mpa)	≥55	≥60	≥60	≥65	≥70
°C U.R.L 0.2Mpa	≥1550	≥1580	≥1640	≥1660	≥1680
L.C(%) (1650 °C /2h)	0-0.5	0-0.4	0-0.3		0-0.2

For and on behalf of
Dashiqiao Yutong Refractories Co.Ltd
大石桥宇通耐火材料有限公司
孟新宇
Authorized Signature(s)