



DASHIQIAO YUTONG REFRACTORIES CO., LTD.

HETUN VILLAGE, GUANTUN TOWN, 115100 DASHIQIAO, YINGKOU, LIAONING, CHINA
Tel: 0086-417-5616187/5616188/5616189 Email: yutong_jessica@hotmail.com
Web: www.yutongrefractory.com

Ref :

TECHNICAL DATA SHEET

Magnesite Chrome bricks

Brand Index	16	12	8
MgO(%)	≥62	≥66	≥72
SiO2 (%)	≤4.0	≤4.0	≤4.0
CaO (%)	≤2.0	≤2.0	≤2.0
Al2O2 (%)	≤6.0	≤6.0	≤5.0
Fe2O3 (%)	≤8.0	≤7.0	≤6.0
Cr2O3	≤16.0	≤12.0	≤8.0
°C U.R.L	≥1600	≥1600	≥1550
A.P (%)	≤19	≤19	≤18
B.D(kg/m3)	≥3.0	≥3.0	≥3.0
Cold Crushing Strength Mpa (Mpa)	≥40	≥40	≥40

For and on behalf of
 Dashiqiao Yutong Refractories Co.Ltd
 大石桥宇通耐火材料有限公司

 Authorized Signature(s)