



# DASHIQIAO YUTONG REFRACTORIES CO., LTD.

HETUN VILLAGE, GUANTUN TOWN, 115100 DASHIQIAO, YINGKOU, LIAONING, CHINA

Tel: 0086-417-5616187/5616188/5616189

Email: yutong\_jessica@hotmail.com

Web: www.yutongrefractory.com

Ref :

## TECHNICAL DATA SHEET

|                                                                                                                                                               |                                    |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------|
| NAME                                                                                                                                                          | LARGE CRYSTAL FUSED MAGNESITE 97.5 |
| CHEMICAL FORMULA                                                                                                                                              | MGO                                |
| FORMULA WEIGH                                                                                                                                                 | 40.3                               |
| SPECIFICATIONS                                                                                                                                                |                                    |
| MGO                                                                                                                                                           | 97.5%MIN                           |
| SIO <sub>2</sub>                                                                                                                                              | 0.65%MAX                           |
| CAO                                                                                                                                                           | 1.30%MAX                           |
| FE <sub>2</sub> O <sub>3</sub>                                                                                                                                | 0.65%MAX                           |
| AL <sub>2</sub> O <sub>3</sub>                                                                                                                                | 0.20%MAX                           |
| L.O.I                                                                                                                                                         | 0.20%MAX                           |
| Bulk Density                                                                                                                                                  | 3.45g/cm <sup>3</sup> MIN          |
| Application: steel making, high grade magnesia bricks, magnesia carbon bricks, unshaped refractory materials, including gunning, ramming, repairing mass etc. |                                    |
| The above mentioned product has no poison, no pollution and no cauterization. It's common chemical product.                                                   |                                    |

For and on behalf of  
Dashiqiao Yutong Refractories Co.Ltd  
大石桥宇通耐火材料有限公司  
**孟新宇**  
Authorized Signature(s)