



DASHIQIAO YUTONG REFRACTORIES CO., LTD.
HETUN VILLAGE, GUANTUN TOWN, DASHIQIAO, YINGKOU, LIAONING, CHINA
Tel: 0086-417-5616187/5616188/5616189 Email: lisa.yi@yutongrefractories.com
www.yutongrefractories.com

Ref :

TECHNICAL DATA SHEET

| | |
|---|--|
| NAME | FUSED MAGNESITE 98 (CaO:SiO ₂ =2:1) |
| CHEMICAL FORMULA | MGO |
| FORMULA WEIGH | 40.3 |
| SPECIFICATIONS | |
| MGO | 97.7%MIN |
| SIO ₂ | 0.60%MAX |
| CAO | 1.20%MAX |
| FE ₂ O ₃ | 0.60%MAX |
| AL ₂ O ₃ | 0.20%MAX |
| L.O.I | 0.20%MAX |
| Bulk Density | 3.50g/cm ³ MIN |
| Application: steel making, high grade magnesia bricks, magnesia carbon bricks, unshaped refractory materials, including gunning, ramming, repairing mass etc. | |
| The above mentioned product has no poison, no pollution and no cauterization. It's common chemical product. | |

For and on behalf of
Dashiqiao Yutong Refractories Co.Ltd
大石桥宇通耐火材料有限公司
孟新宇
Authorized Signature(s)