



DASHIQIAO YUTONG REFRACTORIES CO., LTD.
HETUN VILLAGE, GUANTUN TOWN, 115100 DASHIQIAO, LIAONING, CHINA
Tel: 0086-417-5616187 Email: lisa.yi@yutongrefractories.com
www.yutongrefractories.com

Ref :

TECHNICAL DATA SHEET

NAME	DEAD BURNED MAGNESITE 95
CHEMICAL FORMULA	MGO
FORMULA WEIGH	40.3
SPECIFICATIONS	
MGO	95.0%MIN
SIO2	2.00%MAX
CAO	2.00%MAX
FE2O3	1.50%MAX
AL2O3	0.50%MAX
L.O.I	0.50%MAX
Bulk Density	3.15g/cm ³ MIN
Application: steel making, unshaped refractory materials, enamel, polishing agent and adhesive.	
The above mentioned product has no poison, no pollution and no cauterization. It's common chemical product.	

For and on behalf of
Dashiqiao Yutong Refractories Co.Ltd
大石桥宇通耐火材料有限公司
孟新宇
Authorized Signature(s)