



DASHIQIAO YUTONG REFRACTORIES CO., LTD.  
HETUN VILLAGE, GUANTUN TOWN, 115100 DASHIQIAO, LIAONING, CHINA  
Tel: 0086-417-5616187 Email: lisa.yi@yutongrefractories.com  
www.yutongrefractories.com

Ref :

## TECHNICAL DATA SHEET

NAME	MGO BALL
CHEMICAL FORMULA	MGO
FORMULA WEIGH	40.3
SPECIFICATIONS	
MGO	60.0%MIN
SIO2	5.00%MAX
CAO	3.00%MAX
AL2O3	2.00%MAX
L.O.I.	30.0%MAX
MOISTURE	4.00%MAX
SIZE	40X40MM
Application: steel mill, a rotary melting furnace and making, through the splashing cross to protect the furnace to raise the furnace life.	
The above mentioned product has no poison, no pollution and no cauterization. It's common chemical product.	

For and on behalf of  
Dashiqiao Yutong Refractories Co.Ltd  
大石桥宇通耐火材料有限公司  
**孟新宇**  
Authorized Signature(s)