



DASHIQIAO YUTONG REFRACTORIES CO., LTD.
HETUN VILLAGE, GUANTUN TOWN, 115100 DASHIQIAO, LIAONING, CHINA
Tel: 0086-417-5616187 Email: lisa.yi@yutongrefractories.com
www.yutongrefractories.com

Ref :

TECHNICAL DATA SHEET

NAME	MGO BALL
CHEMICAL FORMULA	MGO
FORMULA WEIGH	40.3
SPECIFICATIONS	
MGO	65.0%MIN
SIO2	5.00%MAX
CAO	3.00%MAX
AL2O3	2.00%MAX
L.O.I.	30.0%MAX
MOISTURE	4.00%MAX
SIZE	40X40MM
Application: steel mill, a rotary melting furnace and making, through the splashing cross to protect the furnace to raise the furnace life.	
The above mentioned product has no poison, no pollution and no cauterization. It's common chemical product.	

For and on behalf of
Dashiqiao Yutong Refractories Co.Ltd
大石桥宇通耐火材料有限公司
孟新宇
Authorized Signature(s)