

Ref:

TECHNICAL DATA SHEET

NAME	Magnesium Oxide Carbon Ball
CHEMICAL FORMULA	MGO
FORMULA WEIGH	40.3
SPECIFICATIONS	
MGO	65.0%MIN
С	10.0%-12.0%
SIO2	5.00%MAX
CAO	2.50%MAX
AL2O3	2.00%MAX
L.O.I.	20.0%MAX
SIZE	20-40MM

Application: steel mill, a rotary melting furnace and making, through the splashing cross to protect the furnace to raise the furnace life.

The above mentioned product has no poison, no pollution and no cauterization. It's common chemical product.

For and on behalf of Dashiqiao Yutong Refractories Co.Ltd 大石桥宇通耐火材料有限公司 Authorized Signature(s)