



DASHIQIAO YUTONG REFRACTORIES CO., LTD.  
HETUN VILLAGE, GUANTUN TOWN, 115100 DASHIQIAO, LIAONING, CHINA  
Tel: 0086-417-5616187 Email: lisa.yi@yutongrefractories.com  
[www.yutongrefractories.com](http://www.yutongrefractories.com)

Ref :

## TECHNICAL DATA SHEET

NAME	MgO-CaO Ball (Slag Conditioner)
CHEMICAL FORMULA	MGO
FORMULA WEIGH	40.3
SPECIFICATIONS	
MGO	60.0%MIN
CAO	7.00%MIN
SIO2	4.50%MAX
FE2O3	2.00%MAX
AL2O3	1.00%MAX
L.O.I.	27.0%MAX
SIZE	30-50MM
Application: steel mill, a rotary melting furnace and making, through the splashing cross to protect the furnace to raise the furnace life.	
The above mentioned product has no poison, no pollution and no cauterization. It's common chemical product.	

For and on behalf of  
Dashiqiao Yutong Refractories Co.Ltd  
大石桥宇通耐火材料有限公司  
孟新宇  
Authorized Signature(s)