

ASTM A106 Seamless Steel Pipes



Certification	ISO 9001
Standard	ASTM A106
Grade	Gr.B
Out Diameter (mm)	1/8" - 24" (DN6- DN600)
Wall Thickness (mm)	Sch10 - SchXXS
Length (m)	6M/ 12M or Customized
Ends	Plain/ Bevel/ Threaded/ Grooved
Usage	Water transfer pipes/ Oil pipes and Gas pipes
Surface	Bare/ Black/ Varnish/ Oiled/ Galvanized/ 3PE, etc

ASTM A106 Seamless Steel Pipes Size

DN (mm)	NPS (Inch)	OD (mm)	Schedule												
			10	20	30	STD	40	60	XS	80	100	120	140	160	XXS
6	1/8	10.3							2.41	2.41					
8	1/4	13.7				2.24	2.24		3.02	3.02					
10	3/8	17.1				2.31	2.31		3.2	3.2					
15	1/2	21.3	2.11		2.41	2.77	2.77		3.73	3.73				4.78	7.47
20	3/4	26.7	2.11		2.41	2.87	2.87		3.91	3.91				5.56	7.82
25	1	33.4	2.77		2.9	3.38	3.38		4.55	4.55				6.35	9.09
32	1 1/4	42.2				3.56	3.56		4.85	4.85				6.35	9.7
40	1 1/2	48.3	2.77		3.18	3.68	3.68		5.08	5.08				7.14	10.15
50	2	60.3	2.77		3.18	3.91	3.91		5.54	5.54				8.74	11.07
65	2 1/2	73				5.49	5.49		7.01	7.01				11.13	14.02
80	3	88.9	3.05		4.78	5.49	5.49		7.62	7.62				11.13	15.24
90	3 1/2	101.6				5.74	5.74		8.08	8.08					
100	4	114.3	3.05		4.78	6.02	6.02		8.56	8.56		11.13		13.49	17.12
125	5	141.3				6.55	6.55		9.53	9.53		12.7		15.88	19.05
150	6	168.3	3.4			7.11	7.11		10.97	10.97		14.27		18.26	21.95
200	8	219.1	3.76	6.35	7.04	8.18	8.18	10.31	12.7	12.7	15.09	18.26	20.62	23.01	22.23

250	10	273	4.19	6.35	7.8	9.27	9.27	12.7	12.7	15.09	18.26	21.44	25.4	28.58	25.4
300	12	323.8	4.57	6.35	8.38	9.53	10.31	14.27	12.7	17.48	21.44	25.4	28.58	33.32	25.4
350	14	355.6	6.35	7.92	9.53	9.53	11.13	15.09	12.7	19.05	23.83	27.79	31.75	35.71	
400	16	406.4	6.35	7.92	9.53	9.53	12.7	16.66	12.7	21.44	26.19	30.96	36.53	40.49	
450	18	457	6.35	7.92	11.13	9.53	14.27	19.05	12.7	23.83	29.36	34.93	39.67	45.24	
500	20	508	6.35	9.53	12.7	9.53	15.09	20.62	12.7	26.19	32.54	38.1	44.45	50.01	
550	22	559	6.35	9.53	12.7	9.53		22.23	12.7	28.58	34.93	41.28	47.63	53.98	
600	24	610	6.35	9.53	14.27	9.53	17.48	24.61	12.7	30.96	38.89	46.02	52.37	59.54	

Chemical composition (%)

Grade	C	Si	Mn	P	S
Gr. B	≤0.30	≥0.10	0.29-1.06	≤0.035	≤0.035

Mechanical properties

Grade	Tensile strength (Mpa)	Yield strength (Mpa)	Longitudinal elongation (%)
Gr. B	≥415	≥240	≥30