
# Hansa Yellow RN

# Color TypeMcColor Index No.P.YCAS NO.652Structure:

Monoazo P.Y. 65 6528-34-3



## **Description :**

- Slightly worse than the red light of pigment yellow 83. High hiding power, good light fastness.
- For air drying paint, latex paint, pigment printing paste.

# **Physical Properties :**

Items	Data
Density (g/cm <sup>3</sup> )	1.10-1.40
Specific Surface Area (m <sup>2</sup> /g)	6-20
Oil Absorption (g/100g)	26-62
PH Value	5.1-11
Bulk Density (lb/gal)	9.7-12.4

<b>Fastness Properties</b>	Data
Heat Resistance ( $^{\circ}\!\!\mathbb{C}$ )	210
Light Resistance (Full Shade, 1~8)	5
Weather Resistance (1~5)	3
Acid Resistance (1~5)	3
Alkali Resistance (1~5)	3

# **Applications :**



Remark: •High Recommendation; ©Recommendation; - Limit Suitability

#### **Storage conditions :**

Should be sealed for avoiding light and moisture.

## Package :

25KG/ Kraft Bag

\*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Hangzhou Fancheng Chemical Co.,Ltd Add: No. 37 Jinyi Road, Xiaoshan, Hangzhou, China Tel: +86-571-83531793 http://www.finelandpigment.com/