


## Quinacridone Magenta 202

**Color Type** Quinacridones  
**Color Index No.** P.R.202  
**CAS NO.** 3089-17-6  
**Structure:**



### Description :

- Recommend for engineering plastic, automotive coatings, as well as packaging ink printing and wood coloring. Excellent light and weather fastness, similar performance to R122 in application but more bluish than R122.

### Physical Properties :

Items	Data
Density (g/cm <sup>3</sup> )	1.51-1.71
Specific Surface Area ( m <sup>2</sup> /g )	-
Oil Absorption (g/100g)	34-50
PH Value	3.0-6.0
Bulk Density (lb/gal)	12.6-14.3

Fastness Properties	Data
Heat Resistance ( °C )	300
Light Resistance ( Full Shade, 1~8 )	7-8
Weather Resistance (1~5)	5
Acid Resistance (1~5)	5
Alkali Resistance (1~5)	5
Ester Resistance	5

### Applications :

Inks	Package printing ink	●
Paints	Automotive OEM	●
	Architectural decorative Paint	●
	Industrial	◎
	Powder Coating	◎
Plastic	PC	●
	PO	●
	PA	●
	POM	●
	PBT	●

Remark: ●High Recommendation;  
◎Recommendation; - Limit Suitability

### Storage conditions :

Should be sealed for avoiding light and moisture.

### Package :

10KG-25KG/ Kraft Bag

\*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

**Fineland Chem Co., Ltd**

Add: Xianggong Village, Hezhuang Town, Xiaoshan District, Hangzhou, China

Tel: +86-571-83531793

<http://www.finelandpigment.com/>