

Chrome Antimony Titanium Buff Rutil

| | |
|-----------------|--------------------------|
| Color Type | COMPERF Yellow 2201K |
| Color Index No. | P.Br. 24 |
| C.I. | 77310 |
| Pigment type | (Cr,Sb,Ti)O ₂ |

Description :

This pigment has good thermal stability, light resistance, chemical corrosion resistance, weather resistance, and outstanding infrared reflection function.

Physical Properties :

| Items | Data |
|---------------------------------------|------|
| Specific Gravity (g/cm ³) | 4.5 |
| Tinting Strength | 100 |
| Oil Absorption (g/100g) | 20 |
| PH Value | 7.0 |
| Mean Particle Size | 0.9 |

| Fastness Properties | Data |
|--------------------------------------|------|
| Heat Fastness °C | 800 |
| Light Resistance (Full Shade, 1~8) | 8 |
| Weather Resistance (1~5) | 5 |
| Acid Resistance (1~5) | 5 |
| Alkali Resistance (1~5) | 5 |

Applications :

PVC-P; PVC-U; PUR; LD-PE; HD-PE;
PP; PS; SB; SAN; ABS/ASA; PMMA;
PC; PA; PETP; CA/CAB; UP; Powder
Coatings; Water Based Coatings; Solvent
Based Coatings; Printing Inks

Storage conditions :

Should be sealed for avoiding light and moisture.

Package :

10KG/Kraft Bag

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Hangzhou Fancheng Chemical Co.,Ltd

Add: No. 37 Jinyi Road, Xiaoshan, Hangzhou, China

Tel: +86-571-83531793

<http://www.finelandpigment.com/>