

# Guangdong Blossom Cheer Holdings Limited

## Test Report

No.: 20230805/C3.8-1056

Date: Aug. 23, 2023

Page: 1/1

Sample No:	3.8NMTE	Sampled Date	2023.08.05	Production Date	2023.08.07
Thickness	3.8mm	Sampled Method	Sampling	Sampler	Jinping Chen
Description	Unit	Standards	Result	Decision	
Density	kg/m <sup>3</sup>	2800	807	OK	
MC(Moisture content)	%	4~7	4.09	OK	
Water absorption thickness expansion rate	%(24h)	≤30	22.80	OK	
IB(Internal Binding Strength)	MPa	≥1.2	1.32	OK	
Static bending strength	MPa	≥30	45.63	OK	
modulus of elasticity	MPa	≥2800	3563	OK	
Thickness	mm	3.7±0.1	3.71	OK	
Length	mm	2150±2.0	2151	OK	
Width	mm	920±2.0	921	OK	
Diagonal Tolerance	mm/m	≤1.5	1.0	OK	
Remark:Carbon crystal material and finish door contains batches					
Result: Qualified.					
Tester:		Jinping Chen	Reviewer:		Yongfeng Nai

\*\*\*End of Report\*\*\*